

Kit Code: 64PJB; Base 64PJ9; Curing Agent 941JB

Description: Acrylithane 2.8 DTM is a direct-to-metal polyurethane topcoat formulated for spray applications in areas requiring VOC less than 2.8 lbs./US gallon.

Recommended use: For use on construction equipment, transportation equipment, truck frames, trailers, bulk tanks, chemical trailer applications that require a monocoat topcoat application with a high-quality appearance..

Features:

- Excellent gloss and color retention.
- Good corrosion resistance.
- Resistant to chemical spills and splashes.
- Does not require a primer.

Service temperatures: Maximum, dry service exposure only: 120°C/248°F.

Physical constants:

Color/Shade code: White/10000 (other colors available)
Finish: High gloss
Volume solids: 57% ± 1
Theoretical spreading rate: 310 ft²/US gallon [7.6 m²/liter] – 3 mils [76 microns]
Flash point: 86°F/30°C
Specific gravity: 10.2 lbs/US gallon [1.2 kg/liter]
Touch dry: 1 hours, 68°F/20°C
Through dry: 12 hours, 68°F/20°C
VOC content: 336 g/liter [2.8 lbs/US gallon]
The physical constants stated are nominal data according to the Hempel Group's approved formulas. VOC may be dependent on color.

Application details:

Product / Mix ratio: Base 64PJ9 : Curing agent 941JB / 4 : 1 by volume
Application method: Airless spray / Air spray / Brush or Roller
Thinner (max. vol.): 08NJB DMC (5% for VOC restrictions, otherwise 5%–15%)
Pot life: 4 hours, 68°F/20°C
Nozzle orifice: 0.011" – 0.013" airless; 0.110" or 2.8 MM fluid cap conventional
Nozzle pressure: 2,000 psi [138 bar]
(Airless spray data are indicative and subject to adjustment)

Cleaning of tools: 08320 Medium Reducer
Indicated film thickness, dry: 3 – 4 mils [76 – 102 microns]
Indicated film thickness, wet: 5.2 – 6.9 mils [132 – 175 microns]
Overcoat interval, min: 12 hours, 68°F/20°C
Overcoat interval, max: See Overcoating below

Surface preparation, new build:

- Remove oil and grease etc. thoroughly with suitable detergent.
- Remove salts and other contaminants by high pressure fresh water cleaning.
- Abrasive blasting to Sa 2 (ISO 8501-1:2007) or SSPC-SP 10.
- Surface profile: Medium (G) (ISO 8503-2).

Application conditions:

- Surface must be completely clean and dry at the time of application.
- Ensure adequate ventilation.
- Air and surface temperature must be above the dew point to avoid condensation.
- Paint temperature should be between 59°F – 77°F [15°C – 25°C] for best performance.
- Only apply when air and surface temperature are between 44°F – 100°F [7°C – 38°C]

Overcoating: Sanding or roughening of surface is recommended if overcoating after 2 weeks.

Repair/maintenance:

- Remove oil and grease etc. thoroughly with suitable detergent.
- Remove salts and other contaminants by high pressure fresh water cleaning.
- Clean damaged areas thoroughly by power tool cleaning to SSPC-SP 11 (or St 3, ISO 8501-1) or by abrasive blasting to min. SSPC-SP 6 (or Sa 2, ISO 8501-1) preferably to SSPC-SP 10.
- Remove dust, blast media, and loose materials.
- Feather edges to sound and intact areas.

Additional information:

Mixing/stirring:

Mix thoroughly before use.

Additives:

- 08EJB (21102 Fast Spray Reducer): For viscosity adjustment in non-VOC restricted areas.
- 08320 (21092 Medium Reducer): For temperatures over 70°F/21°F.
- 08DJB (21099 Brush/Roll Additive): Can help application when brushing/rolling.
- Thinning may be necessary when using long spray hoses and/or paint temperatures below 15°C/59°F. This will cause lower film build and longer drying time.
- Alternate reducers such as acetone or DMC may be used to reduce product without adding VOC.

Storage/shelf life:

- Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C.
- Shelf life: 64PJ9, 3 years; 941JB, 2 years.

Safety:

Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult product Safety Data Sheets and follow all local or national safety regulations.

Note:

Acrylithane 2.8 DTM is for professional use only.

Issued by:

Hempel (USA) – 64PJB

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at www.hempel.com (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at www.hempel.com and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at www.hempel.com
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at www.hempel.com

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from www.hempel.com.

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.