

### Kit Code: 15090; Base 15099; Curing Agent 95045

Formerly Jones-Blair 33304

<b>Description:</b>	Chem-O-Pon Epoxy Primer is a polyamide cured, high solids, high build epoxy primer.
<b>Recommended use:</b>	Industrial OEM and maintenance applications requiring a fast drying epoxy primer with a smooth finish that does not require sanding. Can be used direct to metal or as an intermediate coat over zinc rich primers.
<b>Features:</b>	<ul style="list-style-type: none"><li>• High solids.</li><li>• Excellent extended recoatability.</li><li>• Fast drying.</li><li>• Corrosion resistant.</li><li>• Smooth finish.</li></ul>
<b>Service temperatures:</b>	Maximum dry heat exposure: 250°F/121°C.

### Physical constants:

Color/Shade code:	Light Gray/16690 (other colors available)
Finish:	Flat
Volume solids:	55% ± 1
Theoretical spreading rate:	882 ft <sup>2</sup> /US gallon [22 m <sup>2</sup> /liter] – 1 mils [25 microns]
Flash point:	77°F/25°C
Specific gravity:	12.3 lbs/US gallon [1.46 kg/liter]
Viscosity:	20" – 30", Zahn 4
Touch dry:	1 hour, 68°F/20°C
Through dry:	6 hours, 68°F/20°C
VOC content:	383 g/liter [3.2 lbs/US gallon]

*The physical constants stated are nominal data according to the Hempel Group's approved formulas. VOC may be dependent on color.*

### Application details:

Product / Mix ratio:	Base 15099 : Curing agent 95045 / 3 : 1 by volume
Application method:	Airless spray / Air spray / Brush
Thinner (max. vol.):	083JB or 08320 (0-5%) / 083JB or 08320 (5-15%) / 08DJB (5%)
Pot life:	8 hours, 68°F/20°C
Nozzle orifice:	0.015" – 0.019"
Nozzle pressure:	2,000 psi [138 bar] <i>(Airless spray data are indicative and subject to adjustment)</i>
Cleaning of tools:	083JB Chem-O-Pon Thinner or 08320 Medium Reducer
Indicated film thickness, dry:	2.5 – 3.5 mils [63 – 90 microns]
Indicated film thickness, wet:	4.6 – 6.4 mils [115 – 162 micron]
Overcoat interval, min:	2 hours, 68°F/20°C
Overcoat interval, max:	See Overcoating on Page 2

<b>Surface preparation, new build:</b>	<ul style="list-style-type: none"><li>• Remove oil and grease etc. thoroughly with suitable detergent.</li><li>• Remove salts and other contaminants by high pressure fresh water cleaning.</li><li>• Abrasive blasting to Sa 2½ (ISO 8501-1:2007) or SSPC-SP 10.</li><li>• Surface profile: Medium (G) (ISO 8503-2).</li></ul>
--	---

<b>Application conditions:</b>	<ul style="list-style-type: none"><li>• Surface must be completely clean and dry at the time of application.</li><li>• Ensure adequate ventilation.</li><li>• Air and surface temperature must be above the dew point to avoid condensation.</li><li>• Paint temperature should be between 59°F – 77°F [15°C – 25°C] for best performance.</li><li>• Minimum temperature for curing is 44°F/7°C.</li></ul>
--------------------------------	--

<b>Preceding coat:</b>	According to specification.
------------------------	-----------------------------

- Subsequent coat:** According to specification. Recommended systems are: Acrylithane polyurethanes.
- Overcoating:** Can be overcoated without sanding up to 6 weeks after application. Longer times require pressure washing or sanding.
- Repair/maintenance:**
- Remove oil and grease etc. thoroughly with suitable detergent.
  - Remove salts and other contaminants by high pressure fresh water cleaning.
  - Remove dust, blast media, and loose materials.
  - Clean damaged areas by power tool cleaning to minimum St 2 (spot-repairs), or by abrasive blasting to minimum Sa 2, preferably to Sa 2½ (ISO 8501-1:2007) or SSPC-SP 10.
  - Water jetting to steel: Minimum Wa 2 or Wa 2½, (ISO 8501-4).
  - Acceptable flash-rust degree before application: maximum M (atmospheric exposure), preferably L (immersion) (ISO 8501-4).
  - Feather edges to sound and intact areas.
- Additional information:**
- Mixing/stirring:** Power stir the base, then add hardener to base and power stir for 3 minutes.
- Thinning:** May be necessary in the case of very long spray hoses and/or paint temperatures below 59°F /15°C. This will cause lower film build and longer drying time.
- Additives:**
- 99AJB Accelerator at the rate of 1.0 fl oz per mixed gallon can be used to facilitate faster cure times in colder temperature.
- Storage/shelf life:**
- Store in a cool area to ensure full shelf life. Recommended temperature: 75°F/23°C.
  - Shelf life: 15099 and 95045, 3 years.
- Safety:** Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult product Safety Data Sheets and follow all local or national safety regulations.

**Note:** Chem-O-Pon Epoxy Primer is for professional use only.

**Issued by:** Hempel (USA) – 15090

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at [www.hempel.com](http://www.hempel.com) (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at <a href="http://www.hempel.com">www.hempel.com</a> and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from [www.hempel.com](http://www.hempel.com).

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.